

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 7343 (1986): Code of practice for ultrasonic testing of ferrous welded pipes and tubular products [MTD 21: Non-Destructive Testing]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



IS : 7343 - 1986
(Reaffirmed 1995)

Indian Standard

CODE OF PRACTICE FOR
ULTRASONIC TESTING OF FERROUS WELDED
PIPES AND TUBULAR PRODUCTS

(*First Revision*)

First Reprint JUNE 1998

UDC 621.643.2 [669.1-462.2] : 620.179.16 : 006.76

© Copyright 1986

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

Indian Standard

CODE OF PRACTICE FOR ULTRASONIC TESTING OF FERROUS WELDED PIPES AND TUBULAR PRODUCTS

(First Revision)

Non-Destructive Testing Sectional Committee, SMDC 25

Chairman

SHRI N. V. PANDIT

Representing

M. M. Suri & Associates (P) Ltd, Bombay

Members

SHRI E. B. ARDHANARI	Walchandnagar Industries Ltd, Walchandnagar
SHRI D. R. KOLHATEKAR (Alternate)	
SHRI M. K. BANERJEE	Tata Engineering & Locomotive Co Ltd, Jamshedpur
SHRI A. R. HORE (Alternate)	
SHRI S. K. BANERJEE	Steel Authority of India Ltd (Durgapur Steel Plant), Durgapur
SHRI S. K. DUTTA (Alternate)	
SHRI S. BHASKARAN	Bharat Heavy Electricals Ltd, Tiruchirapalli
SHRI D. K. AGARWAL (Alternate I)	
SHRI P. V. SASTRY (Alternate II)	
SHRI S. C. BHAWAL	National Test House, Calcutta
SHRI K. L. BARUI (Alternate)	
DR V. N. BINDAL	National Physical Laboratory (CSIR), New Delhi
DR ASHOK KUMAR (Alternate)	
SHRI T. K. BOSE	Mining & Allied Machinery Corporation Ltd, Durgapur
SHRI S. KUMAR (Alternate)	
SHRI K. P. CHOPRA	Steel Authority of India Ltd (Bhilai Steel Plant), Bhilai
SHRI R. S. DUBEY (Alternate)	
SHRI R. N. DAS	ACC Vickers Babcock Ltd, Durgapur
DEPUTY DIRECTOR (MET 3),	Ministry of Railways
RDSO, LUCKNOW	
CHEMIST & METALLURGIST,	
WR, AJMER (Alternate)	
SHRI S. C. DEY	Central Boilers Board, New Delhi
SHRI D. DUTTA	Indian Tube Co Ltd, Jamshedpur
SHRI V. S. CHANDRASEKHAR (Alternate)	

(Continued on page 2)

© Copyright 1986

BUREAU OF INDIAN STANDARDS

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

(Continued from page 1)

<i>Members</i>	<i>Representing</i>
SHRI V. EASWARN	Steel Authority of India Ltd (R & D), Ranchi
SHRI M. C. JOSHI (<i>Alternate</i>)	
SHRI K. N. KINI	Air India, Bombay
SHRI A. V. KULKARNI (<i>Alternate</i>)	
SHRI N. KOSHI	Ministry of Shipping & Transport
SHRI S. S. MUKHERJEE	Burn Standard & Co Ltd, Howrah
SHRI P. DASGUPTA (<i>Alternate</i>)	
SHRI K. V. NARASIMHA RAO	K. C. P. Ltd, Tiruvottiur
SHRI PRAKASH D. NIRGUDKAR	The Institute of Indian Foundrymen, Bombay
SHRI S. K. AHUJA (<i>Alternate</i>)	
SHRI A. S. PRASAD	Tata Iron & Steel Co Ltd, Jamshedpur
SHRI S. A. HAQUE (<i>Alternate</i>)	
SHRI J. PRASAD	Hindustan Aeronautics Ltd, Bangalore
SHRI T. RANGACHARY (<i>Alternate</i>)	
DR V. RAMASWAMY	Steel Authority of India Ltd (R & D Centre for Iron and Steel), New Delhi
SHRI SUDHAKAR JHA (<i>Alternate</i>)	
SHRI S. RAMASWAMY	Mukand Iron & Steel Works Ltd, Bombay
SHRI D. S. P. RAO	Bharat Heavy Plates & Vessels Ltd, Visakhapatnam
SHRI S. ADIMOORTY (<i>Alternate</i>)	
SHRI B. N. RAY	Ministry of Defence (DGI)
SHRI S. R. MAZUMDAR (<i>Alternate</i>)	
SHRI SANJOY ROY	Central Mechanical Engineering Research Institute, Durgapur
SHRI S. R. BASAK (<i>Alternate</i>)	
SHRI S. R. SAHU	Steel Authority of India Ltd (Bokaro Steel Plant), Bokaro Steel City
SHRI G. C. PRASAD (<i>Alternate</i>)	
SHRI N. L. SAO	Central Mining Research Station (CSIR), Dhanbad
DR B. K. SARKAR	Vikram Sarabhai Space Centre, Trivandrum
SHRI C. R. SATYA (<i>Alternate</i>)	
SHRI R. B. SINGH	Heavy Engineering Corporation Ltd, Ranchi
SHRI N. M. WALECHA	Directorate General of Civil Aviation, New Delhi
SHRI R. R. WAMORKAR	Bhabha Atomic Research Centre, Bombay
SHRI P. C. KULKARNI (<i>Alternate</i>)	
SHRI K. RAGHAVENDRAN,	Director General, ISI (<i>Ex-officio Member</i>)
Director (Stirc & Met)	
	<i>Secretary</i>
	SHRI B. K. MUKHOPADHYAY
	Assistant Director (Metals), ISI

Ultrasonic Testing Standards Subcommittee, SMDC 25 : 3

Convener

SHRI S. RAMASWAMY Mukand Iron & Steel Works Ltd, Bombay

Members

SHRI D. K. AGARWAL Bharat Heavy Electricals Ltd, Bhopal
SHRI S. GOWRISANKARAN (*Alternate*)

(Continued on page 7)

Indian Standard

CODE OF PRACTICE FOR ULTRASONIC TESTING OF FERROUS WELDED PIPES AND TUBULAR PRODUCTS

(First Revision)

0. FOREWORD

0.1 This Indian Standard (First Revision) was adopted by the Indian Standards Institution on 5 February 1986, after the draft finalized by the Non-Destructive Testing Sectional Committee had been approved by the Structural and Metals Division Council.

0.2 This standard is intended to be a guide for the ultrasonic testing of ferrous welded pipes and tubular products. This was first published in 1974. This has now been revised in the light of experience gained since its publication.

0.3 In reporting the result of a test made in accordance with this standard, if the final value, observed or calculated, is to be rounded off, it shall be done in accordance with IS : 2-1960*.

1. SCOPE

1.1 This standard covers procedures for detecting longitudinal and transverse (circumferential) discontinuities in ferrous welded pipes and tubular products using ultrasonic pulse echo-contact and immersion techniques. It is intended to be used for tubular products having outside diameter greater than 12 mm and having an outside diameter to inside diameter ratios less than 2.

1.2 For the purpose of this standard, all the relevant requirements specified in this standard in addition to the requirements specified in IS : 3664-1981† are applicable.

*Rules for rounding off numerical values (revised).


†Code of practice for ultrasonic pulse echo testing by contact and immersion methods (first revision).

2. REFERENCE STANDARD

2.1 A reference specimen of a convenient length shall be prepared from a defect free length of the pipe containing the weld. The pipe shall be identical in material and dimensions to the product under inspection. The weld configuration welding procedure and weld surface finish shall be identical to those of the actual welds to be inspected. Reference defects as described in 2.2 shall be introduced in this length of pipe.

2.2 Longitudinal and transverse notches shall be introduced on the outer (OD) and inner (ID) surfaces of the reference standard. The notches shall be located on the weld. The notches shall be sufficiently separated from each other and from the ends of the tube to avoid mutual interference leading to difficulties in interpretation of reflected signals.

2.2.1 The acceptable notch configurations and the dimensions to be measured are shown in Fig. 1.



NOTE — In figs. 1A, 1B and 1D the sharp corners are for ease of illustration. It is recognized that in normal machining practice a radius will be generated.

FIG. 1 COMMON NOTCH SHAPES

2.2.2 The dimensions of the artificial notches shall be as follows:

Length — 12.5 mm, 25 mm or 38 mm or 50 mm as agreed upon by the contracting parties.

Depth — 3 percent, 5 percent, 10 percent or 12 percent of the nominal wall thickness (subject to a minimum of 0.3 mm) as agreed upon by the contracting parties.

However, for critical application the minimum limit can be agreed upon by the contracting parties to 0.2 mm.

Width — The width shall be as small as practicable, preferably 1.5 mm or less.

Angle — For V-notches, the angle of the notch shall be chosen in relation to the beam angle to be employed during inspection, in order to get maximum reflected signal from the notch.

Tolerances — Tolerance on depth shall be ± 15 percent of the specified depth, subject to a minimum of ± 0.05 mm.

2.2.3 The notch depth shall be measured from the circular tubing surface to the deepest penetration of the notch.

3. CALIBRATION OF APPARATUS

3.1 Using the reference standard specified in 2, the equipment shall be adjusted using suitable angle beam probes to produce readily distinguishable and clearly identifiable indications from both OD and ID notches.

4. PROCEDURE


4.1 During manual operation scanning shall be performed at a minimum gain setting of twice (+ 6dB) the standard level though evaluation of any defect shall be done at the standard sensitivity level. For automated equipment, however, scanning shall be performed at the standard sensitivity level.

4.2 Scanning shall be carried out in two circumferential directions (see Fig. 2). For critical applications, additional scanning in axial directions, shall be subject of mutual agreement between the purchaser and the supplier. The entire volume of the pipe shall be covered for each scan with a minimum overlap of 15 percent between successive scan path.


4.2.1 For circumferential scanning the probe has to move over the weld bead. Therefore, the weld bead has to be ground sufficiently smooth to ensure proper transmission of ultrasonic energy into the weld.

5. INTERPRETATION OF RESULTS

5.1 Indication giving an echo amplitude less than the amplitude of the echo reference notch shall be accepted.



2A Circumferential Scanning in Two Directions



2B Axial (Longitudinal) Scanning in Two Directions

FIG. 2 SCANNING DIRECTIONS

5.2 All indication giving an echo amplitude equal to or greater than the amplitude of the echo from the reference notch shall be considered as suspects and subject to investigation for defects followed by repair. The procedure shall be agreed upon by the contracting parties. After checking the remaining wall thickness, repaired areas shall be retested using the same procedure specified in this standard. Signals lower than the standards shall be considered as acceptable.

5.3 If automated or immersion scanning technique is used, regions giving indication equal to or greater than the reference echo shall be retested manually to determine their acceptability according to 5.1.

6. TEST REPORT

6.1 All the essential details of the inspection data including results and the date on test set-up required for repeating the test shall be included in the report.

(Continued from page 2)

Members

SHRI K. J. SINGH AROBA
DR V. N. BINDAL

DR G. L. DATTA
SHRI S. A. HAQUE
SHRI M. P. MITTAL
SHRI P. P. PURANIK
SHRI D. S. P. RAO

SHRI L. VENKATARAMAN

Representing

Bharat Steel Tubes Ltd, Ganaur
National Physical Laboratory (CSIR), New
Delhi
Institute of Indian Foundrymen, Kharagpur
Tata Iron & Steel Co Ltd, Jamshedpur
Bharat Steel Tubes Ltd, New Delhi
Tata Engineering & Locomotive Co Ltd, Pune
Bharat Heavy Plate & Vessels Ltd,
Visakhapatnam
Bhabha Atomic Research Centre, Bombay

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones: 323 0131, 323 3375, 323 9402

Fax : 91 11 3234062, 91 11 3239399, 91 11 3239382

Telegrams : Manaksanstha
(Common to all Offices)

Central Laboratory:

Plot No. 20/9, Site IV, Sahibabad Industrial Area, SAHIBABAD 201010

Telephone

8-77 00 32

Regional Offices:

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002 323 76 17

*Eastern : 1/14 CIT Scheme VII M, V.I.P. Road, Maniktola, CALCUTTA 700054 337 86 62

Northern : SCO 335-336, Sector 34-A, CHANDIGARH 160022 60 38 43

Southern : C.I.T. Campus, IV Cross Road, CHENNAI 600113 235 23 15

†Western : Manakalaya, E9 Behind Marol Telephone Exchange, Andheri (East),
MUMBAI 400093 832 92 95

Branch Offices:

'Pushpak', Nurmohamed Shaikh Marg, Khanpur, AHMEDABAD 380001 550 13 48

‡Peenya Industrial Area, 1st Stage, Bangalore - Tumkur Road,
BANGALORE 560058 839 49 55

Gangotri Complex, 5th Floor, Bhadbhada Road, T. T. Nagar, BHOPAL 462003 55 40 21

Plot No. 62-63, Unit VI, Ganga Nagar, BHUBANESHWAR 751001 40 36 27

Kalaikathir Buildings, 670 Avinashi Road, COIMBATORE 641037 21 01 41

Plot No. 43, Sector 16 A, Mathura Road, FARIDABAD 121001 8-28 88 01

Savitri Complex, 116 G. T. Road, GHAZIABAD 201001 8-71 19 96

53/5 Ward No. 29, R. G. Barua Road, 5th By-lane, GUWAHATI 781003 54 11 37

5-8-58C, L. N. Gupta Marg, Nampally Station Road, HYDERABAD 500001 20 10 83

E-52, Chitaranjan Marg, C-Scheme, JAIPUR 302001 37 29 25

117/418 B, Sarvodaya Nagar, KANPUR 208005 21 68 76

Seth Bhawan, 2nd Floor, Behind Leela Cinema, Naval Kishore Road,
LUCKNOW 226001 23 89 23

Patliputra Industrial Estate, PATNA 800013 26 23 05

T. C. No. 14/1421, University P. O. Palayam,
THIRUVANANTHAPURAM 695034 6 21 17

NIT Building, Second Floor, Gokulpat Market, NAGPUR 440010 52 51 71

Institution of Engineers (India) Building, 1332 Shivaji Nagar, PUNE 411005 32 36 35

*Sales Office is at 5 Chowringhee Approach, P. O. Princep Street,
CALCUTTA 700072 27 10 85

†Sales Office is at Novelty Chambers, Grant Road, MUMBAI 400007 309 65 28

‡Sales Office is at 'F' Block, Unity Building, Narashimaraja Square,
BANGALORE 560002 222 39 71